



Great Lakes Rubber Company

30573 Beck Rd
Wixom, MI 48393
P: 248.624.5710
F: 248.624.4770

www.greatlakesrubberco.com

SustainSBR-55

51% wt recycled content SBR rubber compound

<u>Physical Properties</u>	<u>Required Value</u>	<u>Median Value</u>	
Specific Gravity ASTM D792-13	---	1.313	g/cm ³
Hardness ASTM D2240-15	---	56	Shore A
Tensile Strength ASTM D412-15a	---	1018	psi
Modulus at 100% ASTM D412-15a	---	277	psi
Elongation at Break ASTM D412-15a	---	520	%
Compression Set ASTM D395 Method B	---	---	%
Cure Type	---	Sulfur	
Date:		9/10/2020	